

MER-KOTE PRODUCTS, INC. -- UNDERLAY-L LIQUID -- 5601-00-618-0258

=====
Product Identification
=====

Product ID:UNDERLAY-L LIQUID

MSDS Date:04/19/1993

FSC:5601

NIIN:00-618-0258

Kit Part:Y

MSDS Number: BVTYG

=== Responsible Party ===

Company Name:MER-KOTE PRODUCTS, INC.

Address:501 S. VAN NESS AVENUE

City:TORRANCE

State:CA

ZIP:90501

Country:US

Info Phone Num:213-775-2461

Emergency Phone Num:213-775

-2461

Preparer's Name:MARK GLENDRANGE

CAGE:1Z429

=== Contractor Identification ===

Company Name:MER-KOTE PRODUCTS INC

Address:501 S VAN NESS AVE

Box:City:TORRANCE

State:CA

ZIP:90501

Country:US

Phone:213-775-2461

CAGE:1Z429

=====
Composition/Information on Ingredients
=====

Ingred Name:STYRENE POLYMER WITH 1,3-BUTADIENE

CAS:9003-55-8

RTECS #:WL6478000

Other REC Limits:NONE RECOMMENDED

Ingred Name:WATER

CAS:7732-18-5

RTECS #:ZC0110000

Other REC Limits:NONE RECOMMENDED

=====

=====
Hazards Identification
=====

Routes of Entry: Inhalation:NO Skin:YES Ingestion:NO
Reports of Carcinogenicity:NTP:NO IARC:NO OSHA:NO
Health Hazards Acute and Chronic:NONE ESTABLISHED
Effects of Overexposure:SLIGHT ALKALI DERMATITIS IN SENSITIVE PEOPLE.
Medical Cond Aggravated by Exposure:NONE

=====
First Aid Measures
=====

First Aid:SKIN CONTACT: SOAP AND WATER FLUSH. EYE CONTACT: FLUSH WITH WATER 15 MINUTES..

=====
Fire Fighting Measures
=====

Flash Point:NONE

=====
Accidental Release Measures
=====

Spill Release Procedures:FLUSH SMALL SPILLS WITH WATER. SOAK LARGER SPILLS WITH ABSORPTIVE MATERIAL AND SWEEP UP.
Neutralizing Agent:NONE SPECIFIED BY MANUFACTURER.

=====
Handling and Storage
=====

Handling and Storage Precautions:STORE IN COOL, DRY PLACE. DO NOT FREEZE.

=====
Exposure Contr
ols/Personal Protection
=====

Respiratory Protection:NONE.
Ventilation:LOCAL EXHAUST: IN ENCLOSED AREAS.
Protective Gloves:YES, IF SENSITIVE.
Eye Protection:GOGGLES.
Other Protective Equipment:NONE.
Work Hygienic Practices:WASH HANDS BEFORE EATING OR SMOKING.
Supplemental Safety and Health
NONE.

=====
Physical/Chemical Properties
=====

HCC:B3
Boiling Pt:B.P. Text:212F,100C
Melt/Freeze Pt:M.P/F.P Text:32.0F,0.0C
Vapor Pres:17.5
Spec Gravity:1
pH:8.5
Viscosi

ty:100 CCS

Evaporation Rate & Reference: